

# BupFoil-XP



<b>Cover Type:</b>	Silicone rubber	
<b>Possible applications:</b>	Counterpart rollers for film extrusion-lamination and embossing	
<b>Hardness Range:</b>	60, 70, 75, 80 Shore A	
<b>Recommended Cover Thickness:</b>	min. 15 mm - max. 25 mm	
<b>Temperature resistance:</b>	Dry:	continuous 180°C / peak 220°C
<b>Properties and advantages:</b>	Excellent deformation recovery. Stable mechanical and dynamical properties on the working range of temperatures. Compatible with High speed processes. Non Staining.	
<b>Chemical resistance:</b>	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Chlorinated solvents: Polar solvents (MEC, ether, acetate,...):	Moderate Good Very good Excellent Good Not suited Moderate
<b>Recommended cleaning products:</b>	(Hot) water, steam, soap and detergents, industrial cleaners, alcohol based cleaners	
<b>Remark:</b>	BupFoil-XPD : double hardness solution	