



Cover Type:	Special rubber	
Possible applications:	press section hard press, hard smoothing press roll	
Hardness Range:	1 PJ	
Recommended Cover Thickness:	Standard 20 mm	
Temperature resistance:	Dry:	continuous 100°C / peak 115°C
Properties and advantages:	Doctorability Wear resistance Impact and marking resistance Profile stability in operation (85 shore D, 100 Shore A)	
Doctoring:	with steel or plastic blades ($T_g > 150^\circ\text{C}$), angle 25 to 28 degrees, load 200 to 300 N/m	
Chemical resistance:	Acid solutions:	Good
	Alkaline solutions:	Good
	Hot water and steam:	Good
	Ozone:	Good
	Oil and grease:	Excellent
	Chlorinated solvents:	Not suited
	Polar solvents (MEC, ether, acetate,...):	Not suited
Remark:	Reference list available on demand Good resistance to standard chemicals normally used in paper machines	