



<b>Cover Type:</b>	Special rubber	
<b>Possible applications:</b>	press section hard press, hard smoothing press roll	
<b>Hardness Range:</b>	1 PJ	
<b>Recommended Cover Thickness:</b>	Standard 20 mm	
<b>Temperature resistance:</b>	Dry:	continuous 100°C / peak 115°C
<b>Properties and advantages:</b>	Doctorability Wear resistance Impact and marking resistance Profile stability in operation (85 shore D, 100 Shore A)	
<b>Doctoring:</b>	with steel or plastic blades ( $T_g > 150^{\circ}\text{C}$ ), angle 25 to 28 degrees, load 200 to 300 N/m	
<b>Chemical resistance:</b>	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Chlorinated solvents: Polar solvents (MEC, ether, acetate,...):	Good Good Good Good Excellent Not suited Not suited
<b>Remark:</b>	Reference list available on demand Good resistance to standard chemicals normally used in paper machines	