



<b>Cover Type:</b>	Special polyurethane	
<b>Possible applications:</b>	<p>Recommended cover quality for spike wheels and for all high-load wheels</p> <p>Certain roller applications under heavy (dynamical) load</p> <p>Stretching rollers for straps, fibre, filament and tissue - hacker rollers for plastic granulate and fibres</p> <p>Steel industry: coil carrier rolls, drive wheels for sinter drums, pressure and edge cutter rings</p> <p>Moulded and technical parts submitted to high (vibration) load</p>	
<b>Hardness Range:</b>	75, 80, 84, 93, 95, 98 Shore A	
<b>Recommended Cover Thickness:</b>	min. 10 mm - max. 20 mm	
<b>Temperature resistance:</b>	Dry:	continuous 80°C / peak 110°C
	Wet:	continuous 40°C / peak 50°C
<b>Properties and advantages:</b>	<p>Remarkable physical properties : abrasion and tear resistance - very high traction and compression moduli</p> <p>Very low heat build-up under dynamic load, very low compression set</p> <p>Resists to high static and dynamic charges</p> <p>Outstanding oil resistance. Resistant to fuel, kerosine en different hydrocarbons</p> <p>Not to be used in wet environment above 50 °C - not recommended for cover thickness over 25 mm</p>	
<b>Chemical resistance:</b>	Acid solutions:	Not suited
	Alkaline solutions:	Not suited
	Hot water and steam:	Not suited
	Ozone:	Good
	Oil and grease:	Excellent
	Aromatic solvents (toluene, benzene,...):	Moderate
	Chlorinated solvents:	Not suited
	Polar solvents (MEC, ether, acetate,...):	Not suited
<b>Recommended cleaning products:</b>	water, soap, industrial cleaners, fuel-based cleaners	
<b>Remark:</b>	Under certain conditions, higher loads are acceptable than those recommended in this data sheet - please contact us for spike wheels or for specific applications	

