

# WoodCoat-SP



<b>Cover Type:</b>	Rubber	
<b>Possible applications:</b>	<p>Production of wood, wood board and wood laminate :</p> <ul style="list-style-type: none"><li>- varnishing and lacquering rollers for water or oil based coatings</li><li>- oiling and staining rollers</li><li>- impregnation rollers</li><li>- catalyst and primer application</li></ul> <p>Possibility to foresee microgrooves up to 80 grooves/inch</p>	
<b>Hardness Range:</b>	40, 45, 50, 55, 60, 65, 70, 80 Shore A	
<b>Recommended Cover Thickness:</b>	min. 12 mm - max. 25 mm	
<b>Temperature resistance:</b>	Dry: Wet:	continuous 100°C / peak 110°C continuous 60°C / peak 70°C
<b>Properties and advantages:</b>	<p>Very good surface wetting and transfer properties</p> <p>Good physical properties and lifetime</p> <p>High purity and homogeneity</p> <p>Excellent oil resistance</p> <p>Easy to grind and to groove</p>	
<b>Chemical resistance:</b>	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,...): Chlorinated solvents: Polar solvents (MEC, ether, acetate,...): Alcohols (ethanol, IPA,...): Ageing resistance:	Moderate Good Good Very good Wyjątkowy Moderate Not suited Not suited Very good Excellent
<b>Recommended cleaning products:</b>	(Hot) water, soap, most industrial cleaners, alcohol, light fuel, turpentine, white spirit	