

HanneDrive HP



| | | |
|---------------------------------------|---|------------------------------|
| Cover Type: | Special rubber | |
| Possible applications: | Helper, Wire Driving roll on a loaded nip position | |
| Hardness Range: | 12, 20, 25, 30, 35, 40, 45, 65 PJ | |
| Recommended Cover Thickness: | max. 25 mm | |
| Temperature resistance: | Dry: | continuous 90°C / peak 120°C |
| Properties and advantages: | Abrasion resistance Resistance to shocks and impacts Hardness and profile stability in operation Developped for high loaded nip position | |
| Doctoring: | HDPE blade: at 1 to 2 mm from surface if loading necessary : angle 16 to 20 deg, load 50 to 70 (maxi 100) N/m (Dry doctoring prohibited) | |
| Possible surface design: | Plain, Suction (S) | |
| Chemical resistance: | Acid solutions: | Good |
| | Alkaline solutions: | Good |
| | Hot water and steam: | Good |
| | Ozone: | Good |
| | Oil and grease: | Excellent |
| | Chlorinated solvents: | Not suited |
| | Polar solvents (MEC, ether, acetate,...): | Not suited |
| Recommended cleaning products: | Good resistance to standard chemicals normally used in paper machines | |
| Remark: | Reference list available on demand | |