## **GelForm-SB**



Cover Type:	Rubber	
Possible applications:	Counterparts for calendering and lamination of PVC and soft plastics (floor covering and sheet)	
	Smooth embossing counterparts for PV0	C-sheet
	Counterparts for plastisol coating and im	pregnation
Hardness Range:	75, 80 Shore A	
Recommended Cover Thickness:	Standard 10 mm	min. 25 mm
Temperature resistance:	Dry: Wet:	continuous 110°C / peak 125°C continuous 80°C / peak 90°C
Properties and advantages:	Good resistance to plasticizers used in the PVC- and soft plastics industry	
	Clear colour, non staining in contact with hot PVC	
	Good physical properties	
	Excellent surface properties, neutral behaviour in contact with PVC and soft plastics	
Chemical resistance:	Acid solutions:	Very good
	Alkaline solutions:	Very good
	Hot water and steam:	Very good
	Ozone:	Excellent
	Oil and grease:	Not suited
	Aromatic solvents (toluene, benzene,):	
	Chlorinated solvents:	Not suited
	Polar solvents (MEC, ether, acetate,): Alcohols (ethanol, IPA,):	Excellent Excellent
	Austroio (otherior, ii A,).	EXOCIOIT
Recommended cleaning products:	Polar solvents (MEK, ethyl acetate, alcohol), detergents - avoid hydrocarbon	



Print date: 27/04/2024