

Press Plast Gold



| | |
|---------------------------------------|--|
| Cover Type: | Special rubber |
| Possible applications: | Tissue paper converting : marrying laminator roller - recommended in case of multi-plyes embossing |
| Hardness Range: | 72 Shore D |
| Recommended Cover Thickness: | min. 10 mm - max. 15 mm |
| Temperature resistance: | Dry: continuous 110°C / peak 125°C |
| Properties and advantages: | Guarantees perfect assembly of the plies even if they are numerous, preserving product softness, thanks to the narrow nip and increased specific pressure No back-side effect (re-embossing of the inner ply) Excellent resistance to mechanical stress Very good abrasion resistance and lifetime Increased release properties |
| Chemical resistance: | Acid solutions: Very good Alkaline solutions: Good Hot water and steam: Good Ozone: Very good Oil and grease: Good Aromatic solvents (toluene, benzene,...): Not suited Chlorinated solvents: Not suited Polar solvents (MEC, ether, acetate,...): Not suited Alcohols (ethanol, IPA,...): Very good Ageing resistance: Very good |
| Recommended cleaning products: | (Warm) water, soap, industrial cleaners and detergents, alcohol, (diluted) acid cleaners |