

Textractor



| | |
|---------------------------------------|---|
| Cover Type: | Special rubber |
| Possible applications: | Textile industry : wet finishing processes on fabric : intermediate and final squeegee foulard rollers Suited for knitted open and tubular fabrics |
| Hardness Range: | 69, 93, 95, 98 Shore A |
| Recommended Cover Thickness: | min. 12 mm - max. 25 mm |
| Temperature resistance: | Dry: continuous 110°C / peak 125°C Wet: continuous 80°C / peak 90°C |
| Properties and advantages: | Outstanding squeezing rate, increased squeezing efficiency, energy saving Homogeneous and constant squeezing Outstanding chemical resistance to main textile auxiliary products High wear and aging resistance, high mechanical stress resistance Non-staining |
| Chemical resistance: | Acid solutions: Good Alkaline solutions: Very good Hot water and steam: Very good Ozone: Very good Oil and grease: Good Aromatic solvents (toluene, benzene,...): Not suited Chlorinated solvents: Not suited Polar solvents (MEC, ether, acetate,...): Not suited Alcohols (ethanol, IPA,...): Very good Ageing resistance: Very good |
| Recommended cleaning products: | (Warm) water, soap, industrial cleaners and detergents, alcohol, acid and alkaline cleaners |